

SUN PROTECTION

POLARIS 2014

Number	Colour	Width mm 2300	Light Properties			Solar Properties			Light Fastness	UV- Trans.	Gtot - value	FC - value
			R	T	A	R	T	A				
2408	powder	✓	57%	31%	12%	50%	25%	25%	6-7	13%	0,41	0,69
8096	rose	✓	52%	21%	27%	47%	23%	30%	6-7	11%	0,42	0,71
8193	living coral	✓	31%	25%	44%	43%	37%	20%	6-7	23%	0,44	0,75
5212	dust rose	✓	36%	18%	46%	28%	21%	51%	6-7	13%	0,48	0,81
8156	orchidee	✓	31%	18%	51%	28%	21%	51%	6-7	15%	0,48	0,81
4175	soft mint	✓	57%	30%	13%	51%	23%	26%	6-7	16%	0,41	0,69
4176	soft bleu	✓	55%	30%	15%	52%	20%	28%	6-7	14%	0,40	0,68
4114	turquoise	✓	18%	11%	71%	17%	14%	69%	6-7	16%	0,52	0,88
5138	ocean	✓	27%	12%	61%	24%	16%	60%	6-7	15%	0,49	0,83
2000	sand	✓	46%	37%	17%	47%	40%	13%	6-7	17%	0,42	0,71
2236	beige	✓	43%	19%	38%	41%	21%	38%	6-7	18%	0,44	0,75
131	vanilla	✓	55%	36%	9%	49%	32%	19%	6-7	11%	0,42	0,71
2322	safari	✓	39%	17%	44%	37%	28%	35%	6-7	17%	0,45	0,76
6106	lemon	✓	53%	32%	15%	49%	28%	23%	6-7	13%	0,41	0,69
2321	hazel	✓	36%	14%	50%	33%	16%	51%	6-7	20%	0,46	0,78
4113	lime	✓	32%	14%	54%	30%	13%	57%	6-7	15%	0,47	0,80
8098	red	✓	17%	13%	70%	16%	12%	72%	6-7	18%	0,52	0,88

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Vertical / Pleated
 Panel Track
 Colour Range 17 (30)
 Composition 100% Trevira CS
 Width 2300 mm
 Cutting Process hot

Pleating Format 20 mm
 Weight 170 g/m²
 Thickness 0,35 mm
 Damp room usable yes
 PVC free yes
 OekoTex yes



Flame
retardant


DIN 4102, B1
 NF P 92-503,M1
 BS 5867 part 2
 UNI 9177 C1
 EN 13773
 NFPA 701



Trevira CS®



suitable for
workstations



B semi-
transparent



by Gerhard
van Cleve
GmbH & Co.KG



Standard 100
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption · All light & solar properties have been tested internally or externally. · Gtot: measure total solar energy that passes through the glazing system and the fabric · Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device got in combination with total energy transmittance of glazing g · Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. · All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.