

SUN PROTECTION

SHADE & DIAMOND 2054 / 2057

Number	Colour	Width mm		Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
		2250	3000	R	T	A	R	T	A			
2054	Shade 1089 white	✓	✓	56%	16%	28%	50%	20%	30%	6-7	>0,45	>0,80
2054	Shade 9169 shell	✓	✓	42%	12%	46%	37%	15%	48%	6-7	>0,45	>0,80
2054	Shade 2368 sand	✓	✓	37%	9%	54%	34%	11%	55%	6-7	>0,45	>0,80
2054	Shade 2367 golden brown	✓	✓	21%	8%	71%	17%	10%	73%	6-7	>0,45	>0,80
2054	Shade 9223 silver-iron	✓	✓	22%	7%	71%	22%	11%	67%	6-7	>0,45	>0,80
2054	Shade 8178 mahagony	✓	✓	25%	11%	64%	23%	14%	63%	6-7	>0,45	>0,80
2054	Shade 9167 shine black	✓	✓	19%	7%	74%	16%	9%	75%	6-7	>0,45	>0,80
2057	Diamond 1106 white	✓	✓	61%	17%	22%	56%	20%	24%	6-7	>0,45	>0,80
2057	Diamond 9222 silver	✓	✓	38%	14%	48%	31%	15%	54%	6-7	>0,45	>0,80
2057	Diamond 2417 bronze	✓	✓	23%	12%	65%	22%	16%	62%	6-7	>0,45	>0,80
2057	Diamond 9221 anthracite	✓	✓	19%	9%	72%	17%	12%	71%	6-7	>0,45	>0,80


All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Vertical / Pleated / Panel Track
 Colour Range 7 + 4
 Composition 100 % PES
 Width 2250 / 3000 mm
 Cutting Process hot

Pleating Format 20 mm
 Weight 160 g/m² | 165 g/m²
 Thickness 0,35 mm
 Damp room usable yes
 PVC free yes
 OekoTex yes



suitable for workstations



B semi-transparent



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.