

SUN PROTECTION

CETUS-SILVER 1099

All printed colours and textures only provide orientation and are not reference pattern.

Number	Colour	Width mm 2850	Light Properties			Solar Properties			UV- Transm.	Gtot - value	FC - value	Openn. factor
			R	T	A	R	T	A				
325	white	✓	56%	10%	34%	57%	10%	33%	5%	0,41	0,58	8%
9102	silver	✓	53%	10%	37%	55%	10%	35%	8%	0,41	0,57	8%
9103	stone	✓	52%	8%	40%	54%	10%	36%	7%	0,42	0,58	8%
9114	flint	✓	46%	7%	47%	52%	11%	37%	5%	0,43	0,62	8%
2371	mushroom	✓	54%	9%	37%	56%	10%	34%	5%	0,41	0,59	8%
2362	chocolate	✓	47%	4%	49%	50%	6%	44%	5%	0,44	0,63	8%
9104	black	✓	47%	5%	48%	51%	8%	41%	5%	0,43	0,60	8%


Usable for Roller / Pleated / Panel Track vertical on request
 Colour Range 7
 Composition 100 % Trevira CS
 Width 2850 mm
 Cutting Process cold
 Processing Direction warp
 Weight 140 g/m²
 Thickness 0,35 mm
 Moisture proofed yes
 Light Fastness 5 - 6



Trevira CS®



suitable for Workstations



B semi-transparent



Fluorocarbon free



SVHC free



PVC free



REACH-compliant



Printable



Energy saving



Bisphenol A free



Conflict Minerals free




Smell free



Standard 100 by Oeko-Tex®



by Gerhard van Clewe GmbH & Co.KG



Aluminium Coating



Flame retardant*

DIN 4102, B1
NF P 92-503, M1

* confirmed by Trevira GmbH.
Further certifications on request.



Halogen free



Formaldehyde free



Lead free

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric
 • FC-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation • All substances, mentioned in the icons, are not used acc. to our recipe. • Finished by a StEP certified company.