

SUN PROTECTION

CLASSIC + CLASSIC B/O LINEN

Number	Colour	Width mm 2300	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value		
			R	T	A	R	T	A					
1211	Classic Print Linen 1098-1041 antique white	✓	51%	24%	25%	46%	27%	27%	6-7	>0,45	>0,70		B semi-transparent
1211	Classic Print Linen 2326-1041 bleached sand	✓	59%	19%	22%	52%	20%	28%	6-7	>0,45	>0,70		
1211	Classic Print Linen 9119-1041 grey	✓	40%	14%	46%	35%	18%	47%	6-7	>0,45	>0,70		
1211	Classic Print Linen 9165-1041 grau	✓	45%	16%	39%	42%	20%	38%	6-7	>0,45	>0,70		
1211	Classic Print Linen 9202-1041 feather gray	✓	46%	14%	40%	40%	15%	45%	6-7	>0,45	>0,70		
1222	Classic b/o Print Linen 1098-1079 antique white	✓	84%	0%	16%	71%	0%	29%	6-7	>0,40	>0,70		
1222	Classic b/o Print Linen 2326-1079 bleached sand	✓	84%	0%	16%	71%	0%	29%	6-7	>0,40	>0,70		
1222	Classic b/o Print Linen 9119-1079 grey	✓	84%	0%	16%	71%	0%	29%	6-7	>0,40	>0,70		
1222	Classic b/o Print Linen 9165-1079 grau	✓	84%	0%	16%	71%	0%	29%	6-7	>0,40	>0,70		
1222	Classic b/o Print Linen 9202-1079 feather gray	✓	84%	0%	16%	71%	0%	29%	6-7	>0,40	>0,70		

All printed colours and textures only provide orientation and are not reference pattern.

Usable for	Roller / Panel Track	Weight	210 g/m ² / 320 g/m ²
Colour Range	5	Thickness	0,32 mm / 0,48 mm
Composition	100 % PES	Moisture proofed	yes
Width	2300 mm	PVC free	yes
Cutting Process	cold	Halogen free	yes
Processing Direction	warp	OekoTex	yes



Standard 100
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.