

# SUN PROTECTION

## ORION 2027

Number	Colour	Width mm 2300	Light Properties			Solar Properties			Light Fastness	UV- Trans.	Gtot - value	FC - value
			R	T	A	R	T	A				
1072	snow	✓	51%	48%	1%	51%	48%	1%	5-6	47%	0,45	0,64
9259	silver	✓	41%	39%	20%	45%	44%	11%	5-6	29%	0,48	0,68
9217	mid grey	✓	29%	28%	43%	38%	38%	24%	5-6	21%	0,51	0,72
9140	griffin	✓	13%	14%	73%	32%	31%	37%	5-6	14%	0,53	0,76
4194	soft mint	✓	49%	47%	4%	48%	47%	5%	5-6	34%	0,46	0,66
5228	powder blue	✓	47%	43%	10%	49%	46%	5%	5-6	33%	0,46	0,66
1114	milk	✓	51%	48%	1%	49%	48%	3%	5-6	33%	0,46	0,65
2443	powder	✓	45%	43%	12%	46%	46%	8%	5-6	31%	0,47	0,67
1113	off white	✓	50%	49%	1%	48%	49%	3%	5-6	35%	0,46	0,77
2000	sand	✓	46%	43%	11%	47%	45%	8%	5-6	30%	0,47	0,67
9103	stone	✓	32%	31%	37%	41%	41%	18%	5-6	24%	0,49	0,71
9264	dark ash	✓	14%	15%	71%	33%	32%	35%	5-6	14%	0,53	0,75

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Vertical / Pleated / Panel Track  
 Colour Range 12  
 Composition 100% Trevira CS  
 Width 2300 mm  
 Pleating Format 20 mm  
 Cutting Process cold

Weight 95 g/m<sup>2</sup>  
 Thickness 0,25 mm  
 Damp room usable yes  
 PVC free yes  
 Halogen free yes  
 OekoTex yes



Flame  
retardant


DIN 4102, B1  
 \* confirmed by  
 Trevira GmbH.  
 Further  
 certifications  
 on request.



Trevira CS®



suitable for  
workstations



B semi-  
transparent



by Gerhard  
van Clewe  
GmbH & Co.KG



Standard 100  
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption · All light & solar properties have been tested internally or externally. · Gtot: measure total solar energy that passes through the glazing system and the fabric · FC-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g · Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. · All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.