

# SUN PROTECTION

## ANTARES BLACK-OUT-COLOUR 1003

Number	Colour	Width mm			Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
		89	127	2300	R	T	A	R	T	A			
2303	ecru	✓	✓	✓	47%	0%	53%	44%	0%	56%	6-7	0,34	0,46
2302	mocha	✓	✓	✓	38%	0%	62%	33%	0%	67%	6-7	0,34	0,46
9139	flint	✓	✓	✓	31%	0%	69%	28%	0%	72%	6-7	0,34	0,46
5173	royal	✓	✓	✓	28%	0%	72%	24%	0%	76%	6-7	0,34	0,46
6115	yellow	✓	✓	✓	35%	0%	65%	30%	0%	70%	6-7	0,34	0,46
8162	red	✓	✓	✓	30%	0%	70%	26%	0%	74%	6-7	0,34	0,46

All printed colours and textures only provide orientation and are not reference pattern.

Usable for  
Colour Range  
Composition  
Width  
Cutting Process  
Processing Direction

Roller / Vertical / Panel Track  
6 (coloured back side)  
100 % PES  
89 / 127 / 2300 mm  
cold  
warp & weft

Weight  
Thickness  
Moisture proofed  
PVC free  
OekoTex

420 g/m2  
0,50 mm  
yes  
yes  
yes




Flame  
retardant

DIN 4102, B1  
NF P 92-503-507,M1  
BS 5867 part 2  
UNI 8456-UNI 9174  
C1 / EN 13772 class 1  
NFPA 702- USA



suitable for  
workstations



D  
black-out



Standard 100  
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.