

## POLARIS 2014

Number	Colour	Width mm 2300	Light Properties			Solar Properties			Light Fastness	UV- Trans.	Gtot - value	FC - value
			R	T	A	R	T	A				
325	white*	✓	54%	45%	1%	50%	43%	7%	6-7	10 %	0,45	>0,70
327	grise*	✓	46%	31%	23%	49%	36%	15%	6-7	15 %	0,46	>0,70
1077	milk*	✓	55%	42%	3%	48%	32%	20%	6-7	11 %	>0,45	>0,70
1037	nature white	✓	57%	28%	15%	51%	27%	22%	6-7	10 %	>0,45	>0,70
9001	dark grey*	✓	30%	20%	50%	42%	32%	26%	6-7	14 %	0,48	>0,70
2408	powder	✓	57%	31%	12%	50%	25%	25%	6-7	13 %	>0,45	>0,70
1035	wool white*	✓	56%	37%	7%	51%	42%	7%	6-7	16 %	0,45	>0,70
9150	iron*	✓	16%	13%	71%	13%	12%	75%	6-7	19 %	>0,45	>0,70
4175	soft mint	✓	57%	30%	13%	51%	23%	26%	6-7	16 %	>0,45	>0,70
5139	aqua	✓	38%	15%	47%	39%	17%	44%	6-7	12 %	>0,45	>0,70
8096	rose	✓	52%	21%	27%	47%	23%	30%	6-7	11 %	>0,45	>0,70
4176	soft bleu	✓	55%	30%	15%	52%	20%	28%	6-7	14 %	>0,45	>0,70
5211	hawaiian ocean	✓	21%	12%	67%	18%	14%	68%	6-7	15 %	>0,45	>0,70
8144	raspberry	✓	51%	28%	21%	49%	26%	25%	6-7	15 %	>0,45	>0,70
5213	lavendel	✓	40%	19%	41%	37%	20%	43%	6-7	16 %	>0,45	>0,70
5138	ocean	✓	27%	12%	61%	24%	16%	60%	6-7	15 %	>0,45	>0,70
8156	orchidee	✓	31%	18%	51%	28%	21%	51%	6-7	15 %	>0,45	>0,70
5212	dust rose	✓	36%	18%	46%	28%	21%	51%	6-7	13 %	>0,45	>0,70
4114	turquoise	✓	18%	11%	71%	17%	14%	69%	6-7	16 %	>0,45	>0,70
8097	bordeaux	✓	19%	12%	69%	18%	11%	71%	6-7	16 %	>0,45	>0,70
5137	marine	✓	5%	9%	86%	9%	12%	79%	6-7	19 %	>0,45	>0,70
9084	black*	✓	5%	11%	84%	7%	13%	80%	6-7	19 %	>0,45	>0,70

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Vertical / Pleated / Panel Track  
 Colour Range 22 (40)  
 Composition 100% Trevira CS  
 Width 2300 mm  
 Cutting Process hot

Pleating Format 20 mm | 32 mm\*  
 Weight 170 g/m<sup>2</sup>  
 Thickness 0,35 mm  
 Damp room usable yes  
 PVC free yes  
 OekoTex yes



Flame  
retardant\*

DIN 4102, B1  
 NF P 92-503-507, M1  
 UNI 8456-UNI 9174 C1  
 EN 13773, BS 5867  
 Part 2, NFPA 701-USA


\*confirmed by Trevira  
 GmbH. Further certifications  
 on request.



Trevira CS®



suitable for  
workstations



B semi-  
transparent



Standard 100  
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.