


SUN PROTECTION

OPAL 2004

Number	Colour	Width mm 2300	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
2452	tofu	✓	39%	43%	18%	42%	42%	16%	5-6	0,49	0,70
9278	rock	✓	33%	37%	30%	27%	38%	35%	5-6	0,56	0,80
9276	linen grey	✓	27%	32%	41%	26%	37%	37%	5-6	0,56	0,80
8198	soft rose	✓	34%	44%	22%	36%	43%	21%	5-6	0,52	0,74
8200	lavender frost	✓	33%	35%	32%	32%	39%	29%	5-6	0,53	0,76
8199	smoke rose	✓	28%	32%	40%	29%	38%	33%	5-6	0,55	0,79
5233	illusion blue	✓	36%	46%	18%	37%	47%	16%	5-6	0,51	0,73
5231	pearl blue	✓	29%	36%	35%	28%	34%	38%	5-6	0,55	0,79
4201	shadow lime	✓	31%	38%	31%	32%	40%	28%	5-6	0,53	0,76
4202	apple green	✓	25%	36%	39%	24%	42%	34%	5-6	0,57	0,81
5232	petrol	✓	15%	23%	62%	16%	24%	60%	5-6	0,60	0,86
9277	iron grey	✓	8%	16%	76%	9%	19%	72%	5-6	0,63	0,90

All printed colours and textures only provide orientation and are not reference pattern.

Usable for	Roller / Vertical / Pleated / Panel Track	Weight	140 g/m ²
Colour Range	12 (24)	Thickness	0,35 mm
Composition	100% PES	Damp room usable	yes
Width	2300 mm	PVC free	yes
Pleating Format	20 mm	Halogen free	yes
Cutting Process	hot	OekoTex	yes



B semi-transparent



suitable for workstations



by Gerhard van Clewe GmbH & Co.KG



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption · All light & solar properties have been tested internally or externally. · Gtot: measure total solar energy that passes through the glazing system and the fabric · FC-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g · Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. · All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.