

SUN PROTECTION

SINFONIA SONOR 2069 + DEVON 2070

Number	Colour	Width mm 2400	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
1110-1037	white Sinfonia Sonor 2069	✓	58%	38%	4%	55%	39%	6%	6-7	0,43	0,61
9267-1037	almond Sinfonia Sonor 2069	✓	43%	29%	28%	40%	32%	28%	6-7	0,49	0,70
9266-1037	linen grey Sinfonia Sonor 2069	✓	42%	30%	28%	41%	29%	30%	6-7	0,49	0,70
4196-1037	wild lime Sinfonia Sonor 2069	✓	46%	29%	25%	45%	30%	25%	6-7	0,47	0,67
1110-1037	white Sinfonia Devon 2070	✓	55%	40%	5%	54%	39%	7%	6-7	0,43	0,61
9267-1037	almond Sinfonia Devon 2070	✓	40%	33%	27%	39%	35%	26%	6-7	0,50	0,71
9266-1037	linen grey Sinfonia Devon 2070	✓	42%	34%	24%	43%	29%	28%	6-7	0,48	0,69
4196-1037	wild lime Sinfonia Devon 2070	✓	46%	36%	18%	48%	36%	16%	6-7	0,46	0,66


All printed colours and textures only provide orientation and are not reference pattern.

Usable for Pleated Blinds
 Colour Range 4 / 4
 Composition 100% PES
 Width 2400 mm
 Cutting Process hot
 Pleating Format 20 mm

Weight 110 g/m²
 Thickness 0,20 mm
 Damp room usable yes
 PVC free yes
 Halogen free yes
 OekoTex yes



Relief-
Printing



A
transparent



by Gerhard van Clewe
GmbH & Co.KG



Standard 100
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption · All light & solar properties have been tested internally or externally. · Gtot: measure total solar energy that passes through the glazing system and the fabric · FC-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g · Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. · All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.