

sustainably finished by van Cleve

SUN PROTECTION



Recycled



REACH-compliant



WETURNED®



Fluorocarbon free*



Smell free*



PVC free*

* free according to recipe



ISO 50001



ISO 9001



ISO 14001

ISO: by Gerhard van Cleve GmbH & Co.KG



ECO ONE FR 1044

Number	Colour	Width mm			Light Properties			Solar Properties			UV Trans- mission	Gtot - value	FC - value
		89	127	3000	R	T	A	R	T	A			
1021	white	✓	✓	✓	84%	15%	1%	72%	16%	12%	0%	0,34	0,58
2025	beige	✓	✓	✓	71%	15%	14%	64%	17%	19%	0%	0,36	0,61
2272	sand	✓	✓	✓	69%	9%	22%	64%	13%	23%	0%	0,36	0,61
9124	light grey	✓	✓	✓	67%	11%	22%	62%	15%	23%	0%	0,37	0,63
9037	manhattan	✓	✓	✓	54%	9%	37%	52%	8%	40%	0%	0,40	0,68
9060	mouse grey	✓	✓	✓	30%	0%	70%	29%	2%	69%	0%	0,47	0,80

Usable for Roller / Panel Track / Vertical
 Colour Range 6
 Composition 100% recycled PES
 Width 89 / 127 / 3000 mm
 Cutting Process cold
 Processing Direction warp & weft

Weight 220 g/m²
 Thickness 0,30 mm
 Moisture proofed yes
 PVC free yes
 OekoTex yes
 Light Fastness 6-7




Flame retardant

DIN 4102, B1

*Further certifications on request.



suitable for Workstations



B semi-transparent



by Gerhard van Cleve GmbH & Co.KG



Standard 100 by Oeko-Tex®

All printed colours and textures only provide orientation and are not reference pattern.

ECO BLACK-OUT FR 1036

Number	Colour	Width mm			Light Properties			Solar Properties			UV Trans- mission	Gtot - value	FC - value
		89	127	3000	R	T	A	R	T	A			
1000	white	✓	✓	✓	84%	0%	16%	71%	0%	29%	0%	0,34	0,58
2025	beige	✓	✓	✓	84%	0%	16%	71%	0%	29%	0%	0,34	0,58
2272	sand	✓	✓	✓	84%	0%	16%	71%	0%	29%	0%	0,34	0,58
9124	light grey	✓	✓	✓	84%	0%	16%	71%	0%	29%	0%	0,34	0,58
9037	manhattan	✓	✓	✓	84%	0%	16%	71%	0%	29%	0%	0,34	0,58
9060	mouse grey	✓	✓	✓	84%	0%	16%	71%	0%	29%	0%	0,34	0,58

Usable for Roller / Panel Track / Vertical
 Colour Range 6
 Composition 100% recycled PES
 Width 89 / 127 / 3000 mm
 Cutting Process cold
 Processing Direction warp & weft

Weight 420 g/m²
 Thickness 0,50 mm
 Moisture proofed yes
 PVC free yes
 OekoTex yes
 Light Fastness 6-7




Flame retardant

DIN 4102, B1

*Further certifications on request.



suitable for Workstations



D black-out



by Gerhard van Cleve GmbH & Co.KG



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.