

SUN PROTECTION

MÉLANGE 2056

Number	Colour	Width mm 2250	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
1080	white	✓	66%	27%	7%	58%	29%	13%	5-6	>0,45	>0,80
2332	cream	✓	51%	26%	23%	50%	18%	32%	5-6	>0,45	>0,80
2421	brown	✓	28%	18%	54%	27%	20%	53%	5-6	>0,45	>0,80
2435	latte	✓	31%	20%	49%	27%	21%	52%	5-6	>0,45	>0,80
2379	chocolate	✓	8%	7%	85%	6%	7%	87%	5-6	>0,45	>0,80
2434	nutwood	✓	12%	14%	74%	9%	11%	80%	5-6	>0,45	>0,80
9230	rock	✓	34%	19%	47%	31%	27%	42%	5-6	>0,45	>0,80
9239	asphalt	✓	18%	18%	64%	15%	25%	60%	5-6	>0,45	>0,80
9238	steel	✓	8%	5%	87%	7%	7%	86%	5-6	>0,45	>0,80
8190	mahogany	✓	29%	21%	50%	24%	23%	53%	5-6	>0,45	>0,80
4190	spectra green	✓	31%	23%	46%	29%	21%	50%	5-6	>0,45	>0,80
4191	kiwi	✓	19%	18%	63%	18%	26%	56%	5-6	>0,45	>0,80


All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Vertical / Pleated / Panel Track
 Colour Range 12
 Composition 100 % PES
 Width 2250 mm
 Cutting Process hot

Pleating Format 20 mm
 Weight 220 g/m²
 Thickness 0,50 mm
 Damp room usable yes
 PVC free yes
 OekoTex yes



suitable for
workstations



B semi-
transparent



Standard 100
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.