

CORONA 1020

Number	Colour	Width mm			Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
		2000			R	T	A	R	T	A			
325	white			✓	51%	46%	3%	45%	49%	6%	5-6	>0,45	>0,70
1077	milk			✓	49%	45%	6%	44%	47%	9%	6-7	>0,45	>0,70
4181	lime blush			✓	46%	29%	25%	44%	27%	29%	6-7	>0,45	>0,70
8177	rose blush			✓	26%	23%	51%	24%	18%	58%	6-7	>0,45	>0,70
2000	sand			✓	48%	42%	10%	43%	45%	12%	6-7	>0,45	>0,70
4182	soft lime			✓	38%	29%	33%	41%	29%	30%	6-7	>0,45	>0,70
9102	silver			✓	44%	38%	18%	40%	40%	20%	6-7	>0,45	>0,70
2416	soft cream			✓	38%	25%	37%	41%	25%	34%	6-7	>0,45	>0,70
4183	jasmin green			✓	35%	31%	34%	31%	30%	39%	6-7	>0,45	>0,70
9219	mid grey			✓	39%	32%	29%	37%	29%	34%	6-7	>0,45	>0,70
2363	beige			✓	46%	40%	14%	42%	42%	16%	6-7	>0,45	>0,70
6112	lemon			✓	34%	22%	44%	29%	25%	46%	6-7	>0,45	>0,70
8176	soft lilac			✓	16%	12%	72%	19%	16%	65%	6-7	>0,45	>0,70
2369	toffee			✓	39%	32%	29%	35%	35%	30%	6-7	>0,45	>0,70
8157	coral			✓	28%	17%	55%	25%	20%	55%	6-7	>0,45	>0,70
8175	orchid blush			✓	20%	9%	71%	22%	12%	66%	6-7	>0,45	>0,70
2362	chocolate			✓	10%	8%	82%	7%	10%	83%	6-7	>0,45	>0,70
5197	royal blue			✓	12%	8%	80%	8%	11%	81%	6-7	>0,45	>0,70
8155	raspberry			✓	24%	18%	58%	20%	20%	60%	6-7	>0,45	>0,70
9114	flint			✓	35%	25%	40%	31%	28%	41%	6-7	>0,45	>0,70


All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Pleated / Panel Track
 Colour Range 20
 Composition 100 % PES
 Width 2000 mm
 Cutting Process hot
 Processing Direction warp

Weight 140 g/m2
 Thickness 0,30 mm
 Moisture proofed yes
 PVC free yes
 Halogen free yes
 OekoTex yes



suitable for workstations



B semi-transparent



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.