

# SUN PROTECTION

## LUNA 1004 II. of II.

Number	Colour	89	Width mm			Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value	
			127	2000	3000	R	T	A	R	T	A				
2141	fleece		✓	✓	✓	✓	68%	14%	18%	67%	17%	16%	6-7	0,35	0,59
2395	powder		-	-	✓	-	61%	15%	24%	58%	16%	26%	6-7	0,39	0,66
2492	linen		-	-	✓	-	48%	14%	38%	43%	15%	42%	6-7	0,43	0,73
2323	sand		✓	✓	✓	✓	42%	12%	46%	40%	15%	45%	6-7	0,44	0,75
2490	cream		✓	✓	✓	✓	62%	15%	23%	59%	16%	25%	6-7	0,39	0,66
2491	hazelnut		✓	✓	✓	✓	41%	12%	47%	41%	15%	44%	6-7	0,44	0,75
2392	sesam		-	-	✓	-	41%	13%	46%	39%	15%	46%	6-7	0,44	0,75
2326	bleached sand		✓	✓	✓	✓	48%	14%	38%	43%	15%	42%	6-7	0,43	0,73
2393	cinder		✓	✓	✓	✓	36%	9%	55%	31%	13%	56%	6-7	0,47	0,80
6116	soft yellow		-	-	✓	-	57%	23%	20%	51%	21%	28%	6-7	0,41	0,69
2396	cappuccino		-	-	✓	-	28%	8%	64%	25%	11%	64%	6-7	0,49	0,83
2293	dark brown		-	-	✓	-	46%	8%	46%	45%	12%	43%	6-7	0,42	0,71

All printed colours and textures only provide orientation and are not reference pattern.

Usable for  
Colour Range  
Composition  
Width  
Cutting Process  
Processing Direction


Roller / Vertical / Panel Track  
12 / 24  
100 % PES  
89 / 127 / 2000 / 3000 mm  
cold  
warp & weft

Weight  
Thickness  
Moisture proofed  
PVC free  
Halogen free  
OekoTex

210 g/m<sup>2</sup>  
0,45 mm  
yes  
yes  
yes  
yes



suitable for Workstations



B semi-transparent



by Gerhard van Clewe GmbH & Co.KG



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.