

SUN PROTECTION

MERKUR-SILVER 2036

Number	Colour	Width mm		Light Properties			Solar Properties			Light Fastness	UV-Trans.	Gtot - value	FC - value	Openn. factor
		2400	2850	R	T	A	R	T	A					
325	white	✓	✓	49%	6%	45%	51%	6%	43%	5-6	6%	0,44	0,62	2%
9102	silver	✓	✓	50%	5%	45%	51%	6%	43%	5-6	4%	0,43	0,62	2%
9103	stone	✓	✓	50%	4%	46%	51%	5%	44%	5-6	3%	0,44	0,62	2%
9114	flint	✓	✓	47%	1%	52%	49%	4%	47%	5-6	2%	0,44	0,63	2%
2371	mushroom	✓	✓	49%	3%	48%	50%	4%	46%	5-6	3%	0,44	0,63	2%
2362	chocolate	✓	✓	47%	1%	52%	50%	4%	46%	5-6	1%	0,44	0,63	2%
9104	black	✓	✓	41%	1%	58%	45%	4%	51%	5-6	1%	0,46	0,66	2%

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Vertical / Pleated / Panel Track
 Colour Range 7
 Composition 100% Trevira CS
 Width 2400 / 2850 mm
 Cutting Process cold
 Pleating Format 20 mm
 Weight 170 g/m²
 Thickness 0,45 mm
 Damp room usable yes



Flame retardant*

DIN 4102, B1
 NF P 92-503-507,M1

* confirmed by Trevira GmbH. Further certifications on request.



Smell free



Conflict Minerals free



Fluorocarbon free



SVHC free



PVC free



Bisphenol A free



Lead free



Formaldehyde free



Halogen free



Trevira CS®



Aluminium Coating



Energy saving



Printable



suitable for workstations



B semi-transparent



REACH-compliant



by Gerhard van Cleve GmbH & Co.KG



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption · All light & solar properties have been tested internally or externally. · Gtot: measure total solar energy that passes through the glazing system and the fabric · FC-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g · Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. · All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation. All substances mentioned in the icons, are not used acc. to our recipe.