

SUN PROTECTION

CLASSIC BLACK-OUT 1151

Number	Colour	Width mm		Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
		2000	3000	R	T	A	R	T	A			
1079	white	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9202	feather gray	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9165	grey	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
1098	antique white	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2326	bleached sand	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9058	anthracite	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2103	beige	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9200	silver lining	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9199	flint grey	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2173	wool beige	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2400	linen	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9119	dark grey	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2399	nomad	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9201	smoke grey	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9198	steel grey	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2401	chocolate	✓	-	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
4172	shadow green	✓	-	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9092	black	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2398	cream pink	✓	-	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
4174	morning mist	✓	-	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
5205	lavender	✓	-	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
5207	imperial blue	✓	-	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
5178	marine	✓	-	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
8167	jester red	✓	-	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58

All printed colours and textures only provide orientation and are not reference pattern.

Usable for
Colour Range
Composition
Width
Cutting Process
Processing Direction

Roller / Panel Track
24
100 % PES
2000 / 3000 mm
cold
warp & weft


Weight
Thickness
Moisture proofed
PVC free
Halogen free
OekoTex

290 g/m²
0,45 mm
yes
yes
yes
yes

290 g/m²
0,45 mm
yes
yes
yes
yes



suitable for Workstations



D black-out



by Gerhard van Clewe
GmbH & Co.KG



Standard 100
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.