

# SUN C PROTECTION

## JUNO 1097

		89	Width mm			Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value	
			127	2300	3000	R	T	A	R	T	A				
1069	white		✓	✓	✓	✓	69%	19%	12%	63%	22%	15%	5-6	0,39	0,56
2274	cream		✓	✓	✓	✓	67%	14%	19%	62%	17%	21%	5-6	0,39	0,56
2336	cream/beige		-	-	✓	-	61%	16%	23%	55%	20%	25%	5-6	0,42	0,60
9154	light grey		✓	✓	✓	✓	59%	14%	27%	52%	18%	30%	5-6	0,43	0,61
2275	sand		✓	✓	✓	✓	61%	16%	23%	56%	19%	25%	5-6	0,42	0,60
2337	brown/nut		-	-	✓	-	42%	19%	39%	36%	22%	42%	5-6	0,51	0,73
9155	mid grey		✓	✓	✓	✓	18%	13%	69%	14%	17%	69%	5-6	0,61	0,87
2276	brown		✓	✓	✓	✓	42%	18%	40%	37%	21%	42%	5-6	0,50	0,71
4139	spring green		✓	✓	✓	✓	45%	16%	39%	41%	19%	40%	5-6	0,48	0,69
9125	slate		✓	✓	✓	✓	13%	11%	76%	10%	14%	76%	5-6	0,62	0,89
2294	nut		✓	✓	✓	✓	44%	17%	39%	38%	20%	42%	5-6	0,50	0,71
5175	aqua		-	-	✓	-	47%	19%	34%	41%	23%	36%	5-6	0,49	0,70
2295	chocolate		✓	✓	✓	✓	27%	13%	60%	21%	17%	62%	5-6	0,58	0,83
4140	petrol		-	-	✓	-	19%	16%	65%	13%	20%	67%	5-6	0,61	0,87

All printed colours and textures only provide orientation and are not reference pattern.

Usable for  
Colour Range  
Composition  
Width  
Cutting Process  
Processing Direction


Roller / Vertical / Pleated / Panel Track  
14  
100 % PES  
89 / 127 / 2300 / 3000 mm  
hot  
warp

Weight  
Thickness  
Damp room usable  
PVC free  
Halogen free  
OekoTex

150 g/m<sup>2</sup>  
0,35 mm  
yes  
yes  
yes  
yes



suitable for  
workstations



B semi-  
transparent



REACH-  
compliant



by Gerhard van Clewe  
GmbH & Co.KG



Standard 100  
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.