

SUN PROTECTION

CORONA 1020


Number	Colour	Width mm 2000	Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			R	T	A	R	T	A			
325	white	✓	51%	46%	3%	45%	49%	6%	5-6	0,43	0,73
1077	milk	✓	49%	45%	6%	44%	47%	9%	6-7	0,43	0,73
8177	rose blush	✓	26%	23%	51%	24%	18%	58%	6-7	0,49	0,83
2416	soft cream	✓	38%	25%	37%	41%	25%	34%	6-7	0,44	0,75
4181	lime blush	✓	46%	29%	25%	44%	27%	29%	6-7	0,43	0,73
2000	sand	✓	48%	42%	10%	43%	45%	12%	6-7	0,44	0,75
9102	silver	✓	44%	38%	18%	40%	40%	20%	6-7	0,45	0,76
2363	beige	✓	46%	40%	14%	42%	42%	16%	6-7	0,44	0,75
9219	mid grey	✓	39%	32%	29%	37%	29%	34%	6-7	0,45	0,76
2369	toffee	✓	39%	32%	29%	35%	35%	30%	6-7	0,46	0,78

Usable for
Colour Range
Composition
Width
Cutting Process
Processing Direction

Roller / Pleated / Panel Track
10
100 % PES
2000 mm
hot
warp

Weight
Thickness
Moisture proofed
PVC free
Halogen free
OekoTex

140 g/m²
0,30 mm
yes
yes
yes
yes



B semi-transparent



by Gerhard van Clewe GmbH & Co.KG



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.