SUN O PROTECTION

STAR-LIGHT 1016

Number	Colour	89	Width mi 127	m 2300	Light Properties R T A			Solar Properties R T A			Light Fastness	Gtot - value	FC - value
1017	white	√	√	√	72%	17%	11%	68%	19%	13%	6-7	0,37	0,42
2169	sand	√	√	√	63%	4%	33%	58%	8%	34%	6-7	0,40	0,55
327	grise	√	√	√	63%	5%	32%	60%	11%	29%	6-7	0,36	0,42
2413	beach	√	√	√	55%	2%	43%	53%	6%	41%	6-7	0,43	0,61
9193	silver	√	√	√	43%	1%	56%	39%	1%	60%	6-7	0,49	0,70
2033	caramel	√	√	√	61%	11%	28%	53%	16%	31%	6-7	0,39	0,49

Usable for Colour Range Composition Width **Cutting Process**

Roller / Vertical / Panel Track Weight 100 % PES 89 / 127 / 2300 mm cold Processing Direction warp & weft

220 g/m² Thickness 0,35 mm Damp room usable yes PVC free yes Halogen free yes yes OekoTex



retardant

DIN 4102, B1



Perlex



workstations



dim-out



compliant







by Gerhard van Clewe GmbH & Co.KG

Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes throught the glazing system and the fabric • Fcvalue: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.

