

SUN PROTECTION

LUNA PURE 2150

Number	Colour	2400 mm	Light Properties			Solar Properties			UV-Transmission	Openness factor	Gtot value	FC value	Darkening performance	Glare control	Night privacy	Visual contact with the outside	Control of solar gains
			R	T	A	R	T	A									
325	white	✓	55%	33%	12%	52%	36%	12%	-	-	0,41	0,69	0	2	2	2	1
1037	nature white	✓	56%	35%	9%	50%	39%	11%	-	-	0,41	0,69	0	2	2	2	1
2453	creme	✓	51%	24%	25%	47%	26%	27%	-	-	0,42	0,71	0	2	2	2	1
9279	cement	✓	46%	24%	30%	44%	25%	31%	-	-	0,43	0,73	0	2	2	2	1
9280	stone	✓	29%	8%	63%	26%	9%	65%	-	-	0,48	0,81	0	2	2	2	1
9290	iron	✓	20%	6%	74%	18%	4%	78%	-	-	0,51	0,86	0	2	2	2	0

All printed colours and textures only provide orientation and are not reference pattern.


Revision 2

Usable for Roller Blinds, Panel Tracks, Pleated Blinds
 Colour Range 6
 Composition virgin-PES Basis
 Width 2400 mm
 Cutting Process hot

Pleating Format 20 mm
 Weight 185 g/m²
 Thickness 0,50 mm
 Damp room usable yes
 PVC free yes
 OekoTex yes



Halogen free



B semi-transparent



suitable for workstations



REACH-compliant



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.