

SUN PROTECTION

TENDENCE 1109

Number	Colour	89	Width mm			Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			127	2300	3000	R	T	A	R	T	A			
1071	vanilla ice	✓	✓	✓	✓	44%	29%	27%	43%	31%	26%	6-7	>0,55	>0,80
2320	cream	✓	✓	✓	✓	46%	31%	23%	43%	32%	25%	6-7	>0,55	>0,80
2372	ivory	✓	✓	✓	✓	46%	28%	26%	43%	26%	31%	6-7	>0,55	>0,80
2371	mushroom	✓	✓	✓	-	39%	26%	35%	37%	25%	38%	6-7	>0,55	>0,80
2311	ginger	✓	✓	✓	-	22%	18%	60%	19%	22%	59%	6-7	>0,55	>0,80
4141	citronelle	✓	✓	✓	-	21%	17%	62%	21%	15%	64%	6-7	>0,55	>0,80
9175	dust grey	✓	✓	✓	-	17%	19%	64%	15%	20%	65%	6-7	>0,55	>0,80
2319	cardamom	✓	✓	✓	-	21%	17%	62%	20%	16%	64%	6-7	>0,55	>0,80
3059	flame	✓	✓	✓	-	24%	26%	50%	21%	31%	48%	6-7	>0,55	>0,80
2365	coffee	✓	✓	✓	-	13%	15%	72%	11%	13%	76%	6-7	>0,55	>0,80
2312	nutmeg	✓	✓	✓	-	18%	14%	68%	16%	17%	67%	6-7	>0,55	>0,80
8143	chili pepper	✓	✓	✓	-	16%	14%	70%	14%	14%	72%	6-7	>0,55	>0,80


All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Vertical / Pleated / Panel Track
 Colour Range 24 (12/12)
 Composition 100 % PES
 Width 89 / 127 / 2300 / 3000 mm
 Cutting Process hot
 Processing Direction warp & weft

Weight 120 g/m2
 Thickness 0,28 mm
 Moisture proofed yes
 PVC free yes
 Halogen free yes
 OekoTex yes



suitable for workstations



A transparent



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.