

SUN PROTECTION

SIRIUS 1037

| Number | Colour | Width mm 3000 | Light Properties | | | Solar Properties | | | Light Fastness | Gtot - value | FC - value |
|--------|--------------|------------------|------------------|-----|-----|------------------|-----|-----|-------------------|-----------------|---------------|
| | | | R | T | A | R | T | A | | | |
| 1122 | snow white | ✓ | 51% | 45% | 4% | 50% | 43% | 7% | 5-6 | 0,41 | 0,69 |
| 9306 | natural grey | ✓ | 24% | 25% | 51% | 27% | 21% | 52% | 5-6 | 0,48 | 0,81 |
| 9299 | cloud grey | ✓ | 35% | 38% | 27% | 32% | 35% | 33% | 5-6 | 0,47 | 0,80 |
| 9298 | grey | ✓ | 17% | 16% | 67% | 15% | 17% | 68% | 5-6 | 0,52 | 0,88 |
| 2474 | soft beach | ✓ | 33% | 39% | 28% | 31% | 37% | 32% | 5-6 | 0,47 | 0,80 |
| 8190 | mahogany | ✓ | 10% | 11% | 79% | 8% | 12% | 80% | 5-6 | 0,54 | 0,92 |
| 2473 | almond | ✓ | 22% | 26% | 52% | 23% | 29% | 48% | 5-6 | 0,50 | 0,85 |
| 2465 | seal brown | ✓ | 8% | 12% | 80% | 9% | 11% | 80% | 5-6 | 0,54 | 0,92 |

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Pleated / Panel Track
Vertical on request
Colour Range 8
Composition 100 % Trevira CS
Width 3000 mm
Cutting Process cold
Processing Direction warp & weft

Weight 155 g/m²
Thickness 0,45 mm
Moisture proofed yes
PVC free yes
Halogen free yes
OekoTex yes

DIN 4102, B1
* confirmed by
Trevira GmbH.
Further certifications
on request.




Flame
retardant



Trevira CS®



suitable for
Workstations



B semi-
transparent



by Gerhard
van Clewe
GmbH & Co.KG



Standard 100
by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.