

CLASSIC BLACK-OUT COLOUR 1161 I. of II.

Number	Colour	89	Width 127	n mm 2000	3000	Light Properties R T A		Solar Properties R T A			Light Fastness	Gtot - value	FC - value	
1126	snow white	√	✓	✓	✓	74%	0%	26%	76%	0%	24%	6-7	0,32	0,46
9202	feather gray	√	✓	✓	✓	42%	0%	58%	38%	0%	62%	6-7	0,49	0,70
9327	ice grey	√	✓	✓	✓	51%	0%	49%	52%	0%	48%	6-7	0,43	0,61
9329	warm grey	✓	✓	✓	✓	41%	0%	59%	42%	0%	58%	6-7	0,47	0,67
9199	flint grey	✓	✓	√	✓	21%	0%	79%	16%	0%	84%	6-7	0,59	0,84
9325	mirage	-	-	√	-	53%	0%	47%	51%	0%	49%	6-7	0,43	0,61
9328	mid grey	✓	✓	✓	✓	23%	0%	77%	21%	0%	79%	6-7	0,57	0,81
9331	wisper grey	✓	✓	✓	✓	38%	0%	62%	36%	0%	64%	6-7	0,50	0,71
9198	steel grey	✓	✓	✓	✓	14%	0%	86%	9%	0%	91%	6-7	0,62	0,89
2400	linen	✓	✓	✓	✓	31%	0%	69%	36%	0%	64%	6-7	0,50	0,71
9092	black	✓	✓	✓	✓	9%	0%	91%	6%	0%	94%	6-7	0,64	0,91
9330	dust grey	-	-	✓	-	23%	0%	77%	25%	0%	75%	6-7	0,55	0,79

Usable for Colour Range Composition Width **Cutting Process** Roller / Panel Tracks 12 (24) coloured back side 100 % PES 89 / 127 / 2000 / 3000 mm

cold Processing Direction warp & weft Weight Thickness Damp room usable PVC free Halogen free OekoTex yes

290 g/m² 0,45 mm yes yes yes



workstations



black-out











by Gerhard van Clewe GmbH & Co.KG

Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes throught the glazing system and the fabric • Fcvalue: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.





CLASSIC BLACK-OUT COLOUR 1161 II. of II.

Number	Colour	89	Width 127	2000	3000	Light Properties R T A		Solar Properties R T A			Light Fastness	Gtot - value	FC - value	
1079	white	✓	✓	✓	✓	75%	0%	25%	75%	0%	25%	6-7	0,32	0,46
4169	ambrosia	-	-	✓	_	33%	0%	67%	30%	0%	70%	6-7	0,53	0,76
2494	oyster	√	✓	✓	✓	66%	0%	34%	63%	0%	37%	6-7	0,38	0,54
5205	lavender	-	-	✓	-	27%	0%	73%	22%	0%	78%	6-7	0,56	0,80
2495	modesty	-	-	✓	-	70%	0%	30%	68%	0%	32%	6-7	0,36	0,51
2173	beige	-	-	✓	-	39%	0%	61%	37%	0%	63%	6-7	0,50	0,71
2326	bleached sand	✓	✓	√	✓	40%	0%	60%	37%	0%	63%	6-7	0,50	0,71
4172	shadow green	-	-	✓	-	48%	0%	52%	49%	0%	51%	6-7	0,44	0,63
9200	silver lining	√	✓	√	√	48%	0%	52%	47%	0%	53%	6-7	0,45	0,64
2401	chocolate	-	-	✓	-	8%	0%	92%	7%	0%	93%	6-7	0,63	0,90
9201	smoke grey	-	-	✓	-	26%	0%	74%	22%	0%	78%	6-7	0,56	0,80
5207	imperial blue	-	-	√	-	17%	0%	83%	11%	0%	89%	6-7	0,61	0,87

Usable for Colour Range Composition Width Cutting Process Roller / Panel Tracks 12 (24) coloured back side 100 % PES 89 / 127 / 2000 / 3000 mm

Cutting Process cold
Processing Direction warp & weft

Weight Thickness Damp room usable PVC free Halogen free OekoTex 290 g/m² 0,45 mm yes yes yes yes





REAChcompliant







Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes throught the glazing system and the fabric • Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.

