SUN O PROTECTION

MÉLANGE 1144

Number	Colour	89	Width mi 127	m 2300	Light Properties R T A			Solar Properties R T A			Light Fastness		FC - value
1080	white	√	✓	√	66%	27%	7%	58%	29%	13%	5-6	0,41	0,59
2332	cream	✓	✓	√	51%	26%	23%	50%	18%	32%	5-6	0,44	0,63
9230	POCK THE RESERVE TO THE PROPERTY OF THE PROPER	√	√	✓	34%	19%	47%	31%	27%	42%	5-6	0,53	0,76
T 2421		✓	✓	√	28%	18%	54%	27%	20%	53%	5-6	0,55	0,79
9239	Lasphalt	√	√	√	18%	18%	64%	15%	25%	60%	5-6	0,61	0,87
2435	- latte	√	✓	√	31%	20%	49%	27%	21%	52%	5-6	0,55	0,79
9238	scel	√	√	✓	8%	5%	87%	7%	7%	86%	5-6	0,64	0,91
2434	nutwood	√	✓	√	12%	14%	74%	9%	11%	80%	5-6	0,63	0,90

Usable for Colour Range Composition Width

Cutting Process Processing Direction warp

Roller / Vertical / Pleated/ Panel Track

100 % PES 89 / 127 / 2300 mm

PVC free Halogen free OekoTex

Weight 220 g/m² Thickness 0,50 mm Damp room usable yes yes

workstations transparent compliant







by Gerhard van Clewe GmbH & Co.KG



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes throught the glazing system and the fabric • Fcvalue: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,6 and g-value of 0,7 according to DIN EN ISO 13363-1. All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.

yes

