

SUN PROTECTION

APOLLO 1007

Number	Colour	Width mm			Light Properties			Solar Properties			UV-Transm.	Gtot - value	FC - value	Openn. factor
		89	127	3000	R	T	A	R	T	A				
325	white	✓	✓	✓	60%	39%	1%	60%	39%	1%	8%	0,41	0,58	3%
1070	nature white	✓	✓	✓	60%	38%	2%	59%	38%	3%	25%	0,41	0,59	3%
9102	silver	✓	✓	✓	49%	29%	22%	54%	34%	12%	21%	0,43	0,62	3%
2000	sand	✓	✓	✓	54%	34%	12%	55%	36%	9%	22%	0,43	0,61	3%
9103	stone	✓	✓	✓	35%	19%	46%	47%	30%	23%	14%	0,46	0,66	3%
2363	beige	✓	✓	✓	52%	32%	16%	53%	34%	13%	19%	0,44	0,62	3%
2370	slime grey	✓	✓	✓	26%	16%	58%	42%	29%	29%	13%	0,48	0,69	3%
2371	mushroom	✓	✓	✓	21%	36%	43%	31%	47%	22%	16%	0,46	0,66	3%
9114	flint	✓	✓	✓	17%	8%	75%	39%	24%	37%	8%	0,50	0,71	3%
2260	espresso	✓	✓	✓	15%	8%	77%	37%	24%	39%	7%	0,51	0,72	3%
9104	black	✓	✓	✓	4%	3%	93%	30%	21%	49%	4%	0,54	0,77	3%
2362	chocolate	✓	✓	✓	6%	4%	90%	31%	22%	47%	5%	0,54	0,76	3%

All printed colours and textures only provide orientation and are not reference pattern.


Usable for Roller / Vertical / Panel Track
 Colour Range 12
 Composition 100 % Trevira CS
 Width 89 / 127 / 3000 mm
 Cutting Process cold
 Processing Direction warp & weft
 Weight 145 g/m²
 Thickness 0,38 mm
 Moisture proofed yes
 Light Fastness 5 - 6



Trevira CS®



suitable for Workstations



B semi-transparent



Fluorocarbon free



SVHC free



PVC free



REACH-compliant



Printable



Energy saving



Bisphenol A free



Conflict Minerals free



Smell free



Standard 100 by Oeko-Tex®



by Gerhard van Cleve GmbH & Co.KG



Flame retardant*

DIN 4102, B1
 NF P 92-503, M1
 DIN EN ISO 13501-1
 UNI 8456-UNI 9174, C1

* confirmed by Trevira GmbH. Further certifications on request.



Halogen free



Formaldehyde free



Lead free

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric
 • FC-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation • All substances, mentioned in the icons, are not used acc. to our recipe. • Finished by a STeP certified company.